



Product Data

Energrease EP 2

Bearing Grease

Description

BP Energrease EP2 is an extreme pressure, lithium-based, general-purpose industrial grease of an NLGI No. 2 consistency.

Application

Energrease EP2 is recommended as a general-purpose grease in all heavily loaded or shock-loaded plain and anti-friction bearings or where an extreme pressure additive is required on industrial plant and earthmoving equipment. The product is suitable for operating temperatures between -25°C to 120°C

Advantages

- High mechanical stability – the grease keeps its consistency in service ensuring long lubricant life
- Good adhesion – continuous lubrication and reduced consumption as film stays between lubricated surfaces
- Good water resistance – the grease film remains on the surface even in the presence of water
- Resistant to copper and steel corrosion – helps prevent rust and oxidation on metal surfaces
- Excellent EP and anti-wear properties – protects equipment against extreme loading and helps minimise bearing component wear

Typical Characteristics

Name	Method	Units	Energrease EP 2
Appearance	Visual	-	Smooth & Homogeneous
Colour	Visual	-	Amber
Consistency	ASTM D217	NLGI Grade	2
Viscosity, Kinematic 40 °C	ASTM D445	mm ² /s	160
Dropping Point	IP 396	°C	200
Thickner	-	-	Lithium
Worked Penetration((60 strokes @ 25°C / 77°F)	ASTM D217	0.1 mm	275
Water Wash-out (1 hr/79°C)	ASTM D1264	% wt loss	2.1
Copper Corrosion, 24hrs @ 100C	ASTM D130	Rating	1a
Rust Prevention, grease (Emcor)	IP 220	Rating	0/0
Oil separation 168hrs@40°C	IP 121	% wt	2.2
For Ball weld Load	ASTM D 2596	Kgf	250

Name	Method	Units	Energrease EP 2
Four ball wear scar (1hr, 40Kg)	IP 239	mm	0.44

Subject to usual manufacturing tolerances.

Energrease EP 2

07 Mar 2019

BP, the BP logo and related marks are trademarks of BP p.l.c., used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Industrial , Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

www.castrol.com/industrial